

Carboxyl Methyl Cellulose(CMC) CMC ceramic grade

CMC content (on dry basis)	50 - 60 %
Degree of substitution (D.S)	0.75 – 0.85
Moisture content	max 8 %
Viscosity (2 % solution 20°C) Brookfield	3000 - 6000 cps
pH (1% solution)	7-10.5
Density (gr/lit)	400-700
Appearance	Free flowing powder