

Carboxyl Methyl Cellulose(CMC) CMC paint grade

CMC content (on dry basis)	min 60 %	min 60 %
Degree of substitution (D.S)	0.60 – 0.70	0.60 – 0.70
Moisture content	max 8 %	max 8 %
Viscosity (2 % solution 20°C) Brookfield	300 cps	1500 cps
pH (1% solution)	7 – 10.5	7 – 10.5
Density (gr/lit)	400 - 700	400 - 700
Appearance	Free white flowing powder	Free white flowing powder